



Between the World
and The Weather
Since 1928

Ram 203 Membrane Protection Course

PRODUCT DESCRIPTION

Barrett Ram 203 Membrane Protection Course is a multi-purpose SBS polymer-modified, fiberglass reinforced asphalt membrane with sanded surfaces, top and bottom. The polymer modification enhances this products elongation, elastic and flexibility properties. The fiberglass reinforcement gives the composite membrane the tensile strength and toughness necessary to accommodate moderate exposures.

This medium-duty membrane is utilized as a protection course in various waterproofing applications, including Barrett's Ram-Tough 250 waterproofing system. Ram 203 is typically installed into the top coating of the waterproofing membrane system. It is compatible with hot or cold applied asphalt bitumens.

FEATURES

- Enhanced physical properties through polymer modification
- Consistent premium quality
- Superior elongation and cold-temp flexibility properties
- Excellent strength properties

BENEFITS

- Flexibility makes installation easier
- Polymer modification reduces potential for thermal stress
- Resists moderate construction traffic
- Adapts to extreme temperature ranges
- Compatible with all Barrett hot and cold applied adhesives

PACKAGING

| | |
|-----------------------|----------------------------------|
| Roll width | 39 inches (1m) |
| Roll length | 49 ft. (14.9m) |
| Roll size | 159 sq.ft. (14.8m ²) |
| Net coverage | 150 sq.ft. (13.9m ²) |
| Roll weight | 90 lbs.(40.8 kg) |
| Pallet size | 48" x 48" (1.2m x 1.2m) |
| Rolls per pallet | 30 |
| Weight per pallet | 2700 lbs.(1224.7kg) |
| (approx.) | |
| Pallets per truckload | 20 (approx.) |

TYPICAL PHYSICAL PROPERTIES

| Property | Test Method | Typical Value |
|-----------------------------------|-------------|----------------|
| Max. Load at 0±3.6°F (lbf/in) | ASTM D-6163 | 91 (15.9 kN/m) |
| Elongation at 0±3.6°F (%) | ASTM D-6163 | 4.5 |
| Max. Load at 73.4±3.6°F (lbf/in) | ASTM D-6163 | 41 (7.2 kN/m) |
| Elongation at 73.4±3.6°F (%) | ASTM D-6163 | 3.7 |
| Tear Strength at 73.4±3.6°F (lbf) | ASTM D-6163 | 73 (12.8 kN/m) |
| Low Temp. Flex 0°F Max. | ASTM D-6163 | -15 (26.1°C) |
| Dimensional Stability (%) Max. | ASTM D-6163 | <0.1 |
| Compound Stability Temp (°F) | ASTM D-6163 | 250 (121°C) |
| Thickness (mm) | - | 2.2mm/86mils |
| Reinforcement | - | fiberglass |

APPLICATION GUIDELINES

When installing Ram 203, press the sheet into the hot or cold bitumen, making sure that it is totally adhered to its substrate. Wrinkles, buckles, fishmouths, etc. are to be cut out and repaired. Ram 203 shall over lap the proceeding sheet by a minimum of 2 inches (50.8mm). End laps shall be minimum 6 inches (152.4 mm).

STORAGE

All material should be stored on end with its original label and out of the weather. If this material is to be stored outside, it is to be stored on end, elevated off the deck or ground and covered with an opaque, breathable and waterproof cover.

APPLICATION PRECAUTIONS

- Do not apply to wet or damp surfaces
- Do not torch apply
- Avoid contact with petroleum products, oils, grease, animal fats and other foreign materials which could affect this products performance.
- Not for use with potable water collection systems.
- **READ MATERIAL SAFETY DATA SHEET BEFORE USING**
- **FOR PROFESSIONAL ROOFING CONTRACTOR USE ONLY**

PRODUCT SAFETY INFORMATION

Ram 203 Membrane Protection Course offers no unusual health or safety risks for a product of this nature. As with any roofing process, proper ventilation, clothing and eye protection is important.

For specific information, contact the Barrett Company for a current Material Safety Data Sheet on this product.

The user should not assume that all safety measures are indicated or that other measures may not be required.

Note

Metric conversions are rounded and may not be exact.

All statements, information and data given herein are believed to be accurate and reliable, but are presented without guaranty, warranty or responsibility of any kind, expressed or implied, except as may be indicated herein. Statements or suggestions concerning possible uses of our products are made without representation or warranty that any such use is free of patent infringement and are not recommended to infringe any patent.

August 2008