PolyFelt 125 VP

Reinforcement Fabric

Description

PolyFelt 125 is a 16 mil lightweight thermally bonded spun laid non-woven fabric reinforcement.

Uses

RamTough 250 & KLB-100 - Is Installed as a reinforcement fabric between the first and second layers.

Coverage

1,073 sq ft per roll

Properties

Description	Measurement	Test Method
Color	Gray	
Thickness	16 (mils) (0.406 mm)	ASTM D-1777
Mat Weight	2.2 oz./ sq yd (62.4 g)	
Tensile Strength		
Warp (MD) lbs./in.	78 lbs./in (35.4kg)	ASTM D-5034
Fill (CMD) lbs./in.	85 lbs./in (38.6kg)	ASTM D-5034
Elongation at Break		
Warp (MD) lbs./in.	58 lbs./in (26.3kg)	ASTM D-5034
Fill (CMD) lbs./in.	54 lbs./in (24.5kg)	ASTM D-5034
Trapezoid Tear		
Warp (MD) lbs./in.	23.8 lbs./in (10.8kg)	ASTM D-1117
Fill (CMD) lbs./in.	24.9 lbs./in (11.3kg)	ASTM D-1117
Puncture Resistance	31 Lbs (14.1kg)	ASTM D-4830

Packaging

39.4”x327’
Roll Weight 22 lbs
25 rolls per pallet

LIMITED WARRANTY: Barrett warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Barrett makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to The Barrett Company, LLC. Barrett to replace or to refund the purchase price of the quantity of Barrett proven to be defective, and Barrett shall not be liable for any loss or damage.

20.1
Document: KF-01011

Keene Family of Companies
800 | 647 | 0100
F 908 | 647 | 0278